



PO Box 6256  
Mobile AL, 36606  
1-800-771-6643

## PRODUCT DATA SHEET

### Acrylic Clear Gloss 230

#### DESCRIPTION

Acrylic Clear Gloss elastomeric coating is a translucent skylight sealer.

#### ADVANTAGES

- Extremely tough, durable, UV resistant protective sealant.
- Excellent water resistance.
- Good bridging qualities over hairline cracks and small openings.
- Excellent adhesion and binding qualities.
- Outstanding resistance to dirt collection and pollutants.
- Keeps surface clean thereby reducing maintenance costs.
- Environmentally safe.

#### BASIC USES

Acrylic Clear Gloss 230 is used with the AWS metal roof coating system to help seal and recondition skylights. Note, if skylights are cracked, the AWS 230 is not sufficient. In this case the skylight should be replaced.

#### INSTALLATION

All surfaces to be coated must be cleaned properly. Power washing is recommended. Any existing coating must be checked for good adhesion. Before application, any loosely adhered coating must be removed and bare surfaces must be prepared, cleaned and checked for compatibility.

Acrylic Clear Gloss 230 is ready to use. Thinning is not required or recommended.

- Spray: Airless Sprayer, 1/2 g.p.m. capacity with a #517 tip.
- Brush: Good quality synthetic bristle brush.
- Roller: Long nap roller.

#### WARRANTY

American WeatherStar warrants that the material supplied will meet or exceed physical properties as published. The contractor guarantees that workmanship will be free of defects in coating application. Since performance of previously installed substrate is beyond the control of American WeatherStar or the contractor, requests for additional warranty coverage shall be subject to prior approval by American WeatherStar.

#### MAINTENANCE

Periodic maintenance of all American WeatherStar products, including cleaning, will ensure extended service life and maintain reflectivity.



PO Box 6256  
Mobile AL, 36606  
1-800-771-6643

## PRODUCT DATA SHEET

### Acrylic Clear Gloss 230

#### TECHNICAL DATA

<b>Color:</b>	Translucent
<b>Viscosity:</b>	3000 CPS
<b>Weight:</b>	8.7 lbs. per gallon.
<b>Percent Solids by Volume:</b>	45% ± 2%
<b>Flash Point:</b>	NA
<b>Hardness, Shore A:</b>	60
<b>Coverage:</b>	100 sq.ft. per gallon, depending on porosity of surface.
<b>Recommended Coverage:</b>	The number of coats depends on surface porosity.
<b>Drying Time:</b>	6-12 hours
<b>Packaging:</b>	5 gallon buckets, 55 gallon drums