



PO Box 6256
Mobile AL, 36606
1-800-771-6643

PRODUCT DATA SHEET

DTM 3000

DESCRIPTION

DTM 3000 Acrylic Enamel is an interior/exterior 100% acrylic high gloss enamel. It is extremely durable, corrosion and chemical resistant, suitable for commercial, industrial, and residential use.

ADVANTAGES

- High Gloss
- Non-yellowing
- High Durability
- Fast Drying
- Low VOC
- Use on Prepared Metal

BASIC USES

DTM 3000 Acrylic Enamel is suitable for interior and exterior surfaces, steel, galvanized metal, and aluminum.

INSTALLATION

All surfaces to be coated must be cleaned properly. Power washing is recommended. Any existing coating must be checked for good adhesion. Before application, any loosely adhered coating must be removed and bare surfaces must be prepared, cleaned and checked for compatibility.

Dull glossy surfaces with sandpaper or steelwool. Rusting surfaces must be cleaned of loose rust by wire brushing or sand blasting. Prime with DTM primer for maximum corrosion resistance.

May be applied by brush, roller or spray, Stir material thoroughly before using. Paint at temperature between 50 degrees F and 95 degrees F. Allow 4 to 6 hours before recoating. Dampness and humidity will directly effect drying time. Clean equipment and area with soap and water.

WARRANTY

American WeatherStar warrants that the material supplied will meet or exceed physical properties as published. The contractor guarantees that workmanship will be free of defects in coating application. Since performance of previously installed substrate is beyond the control of American WeatherStar or the contractor, requests for additional warranty coverage shall be subject to prior approval by American WeatherStar.



PO Box 6256
Mobile AL, 36606
1-800-771-6643

PRODUCT DATA SHEET

DTM 3000

MAINTENANCE

Periodic maintenance of all American WeatherStar products, including cleaning, will ensure extended service life and maintain reflectivity.

TECHNICAL DATA

Colors:	White / May be tinted to custom colors
Vehicle Type:	100% Acrylic
Gloss:	75-80 at 60 degrees
Weight:	10.19 lbs. per gallon
Vol Solids:	36.40%
Weight Solids:	49.13%
P.V.C.:	19.42%
Flash Point:	NA
Viscosity:	1500 cps
Dry Time:	To Touch in 1 HR To Recoat in 4-6 HRS
V.O.C.:	125 gm/L
Clean Up Solvent:	Water