



PO Box 6256
Mobile AL, 36606
1-800-771-6643

PRODUCT DATA SHEET

Fabric Bond 930

DESCRIPTION

Fabric Bond 930 is designed to be a bonding agent to secure polyester fabric to roof surfaces.

ADVANTAGES

- Seals asphaltic surfaces with little or no bleed through.
- Excellent adhesion to various surfaces.
- Easy to use, easy clean up, non-toxic and VOC compliant water based coating.
- Must be top coated with one of WeatherStar Coatings top coats.

BASIC USES

Great as a primer over Asphalt, concrete, wood, tile, metal and virtually any clean, dry, non-silicone surface. Also used for installing AWS Fabric to any roof surface before applying top coat.

INSTALLATION

All surfaces to be coated must be clean, dry and free of any oil, grease or dirt. Pressure washing is recommended for older coatings. Do not apply within two hours of sunset, rain, fog or freezing temperatures.

Fabric Bond 930 is ready to use. Thinning is not required or recommended.

- Spray: Airless sprayer. 2000 p.s.i., 2 g.p.m. capacity with a #027-#031 tip.
- Brush: Good quality synthetic bristle brush.
- Roller size depends on surface condition:
 - Short nap for smooth surfaces.
 - Medium nap for more porous surfaces.

WARRANTY

American WeatherStar warrants that the material supplied will meet or exceed physical properties as published. The contractor guarantees that workmanship will be free of defects in coating application. Since performance of previously installed substrate is beyond the control of American WeatherStar or the contractor, requests for additional warranty coverage shall be subject to prior approval by American WeatherStar.

MAINTENANCE

Periodic maintenance of all American WeatherStar products, including cleaning, will ensure extended service life and maintain reflectivity.



PO Box 6256
Mobile AL, 36606
1-800-771-6643

PRODUCT DATA SHEET

Fabric Bond 930

TECHNICAL DATA

Color:	Blue
Viscosity:	600-800 CPS
Weight:	8.38 lbs. per gallon
Percent Solids by Weight:	48% \pm 2%
Flash Point:	NA
Recommended Coverage:	Depends on substrate: See application specifications for each surface.
Dry Time:	12 to 24 Hours
Packaging:	5 gallon buckets